

TECHNICAL INFORMATION SHEET

Typical Physical Properties

	ASTM Test Method	StealthWrap™
Color		Carbon
Thickness, gauge	F2251-13	150
Impact Strength Peak Load (lbf)	D3763-15	33
% Clarity	D1746-15	0-4%
% Total Transmittance	D1003-13	0-4%
Coefficient of Friction (Film/stainless, kinetic)	D-1894-95	0.132
Burst Strength, psi	D3763-15	18
		LD/TD
Tensile Strength (x1000 psi)	D-882-95	15/18

LD = Longitudinal Direction/ TD = Transverse Direction

*Near Perfect Concealment

This information represents our best judgement based on the work done. The company assumes no liability whatsoever in connection with the use of information or findings contained herein. Current data is based on limited samples and is subject to modification pending finalization.



02 9452-3566
sales@getpacked.com.au